



CE604 PAVEMENT SEALANT

CONCRETE & ASPHALT

ITEM NUMBER CE604

DESCRIPTION

CE604 Pavement Sealant is a two-component, 100% solids, moisture-insensitive, low viscosity, low modulus, flexible concrete and asphalt crack sealant.

INDUSTRY USES

Use to gravity-fill asphalt and concrete cracks on airport runways, taxiways, and roadways and pavements.

BENEFITS AND FEATURES

- Compatible with CE330 Epoxy Binder for High Friction Surface Treatment (HFST) applications.
- Flexible and durable in all climates
- Made in America
- Moisture Tolerant and outstanding weathering.
- Solvent Free. 100 % solids. No VOCs
- Convenient 1:1 mix ratio by volume
- Chemical resistant against intermittent fuel and oil spills
- Concrete grey or black

PACKAGING

- 1 gal / 3.8 L units
- 10 gal / 38 L units
- 600 ml cartridge

TECHNICAL DATA

Shelf Life:	2 years year in original unopened container.
Storage Conditions:	40°F – 95°F (5°C – 35°C).
Condition material to:	65°F – 85°F (18°C – 29°C) before using.
Mix Ratio	1:1 by volume
Viscosity	1000-1500 cps
Gel Time (60 g mass)	15 minutes
Tack Free Time (73°F or 23°C)	<3 hours
Tensile Properties (ASTM D638), 7-day cure	
Tensile Strength:	1,200 psi (8.3 MPa)
Tensile Elongation:	75%
Adhesion to Concrete (ACI503r, ASTM C1583)	300 psi (2.07 MPa)
Adhesion to Metal (ASTM D4541)	500 psi (3.45 MPa)
Compressive Properties (ASTM C579), 7-day cure	
Compressive Strength:	3,000 psi (20.7 MPa)
Compressive Modulus (ASTM D695)	80,000 psi (552 MPa)
Shrinkage on Cure (ASTM D2566)	0.001
Thermal Compatibility (ASTM C884)	Pass
Jet Fuel Absorption (ASTM D570)	0.2% (24 hr)
Water Absorption (ASTM D570)	0.2% (24 hr)

APPLICATION

MIXING: Mix only the amount of material that can be used within its pot life. Proportion each component carefully into a clean container. Mix thoroughly for 3 minutes with a Jiffy mixer on low speed (400-600rpm). Scrape the sides and bottom of the container. To prepare an epoxy patching mortar, slowly add 4-5 parts of oven-dried silica sand to 1 part of mixed epoxy by volume. Mix only until all aggregate is wetted out.

TO GRAVITY FEED CRACKS: Pour mixed epoxy into cracks. Repeat until completely filled. Broadcast oven-dry silica sand immediately to provide a rough surface profile for High Friction Surface Treatment using CE330 Epoxy Binder.



CE604 PAVEMENT SEALANT

TO PATCH AND GROUT: Prime substrate with neat mixed epoxy if necessary. Place epoxy mortar using trowels before primer becomes tack-free.

LIMITATIONS

Minimum substrate application temperature is 40°F (5°C). Do not thin. Solvents will prevent proper cure.

CLEAN UP

Collect with absorbent material. Flush area with water. Dispose of in accordance with local, state and federal disposal regulations. Uncured material can be removed with CE Natural Clean or other approved solvent. Cured material can only be removed mechanically.

HANDLING PRECAUTIONS

Refer to the Safety Data Sheet for CE604 before using.

LIMITED WARRANTY

All information provided by Cornerstone Construction Material LLC (CCM) concerning CCM products, including but not limited to, any recommendations and advice relating to the application and use of CCM products, is given in good faith based on CCM's current experience and knowledge of its products when properly stored, handled and applied under normal conditions in accordance with CCM's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of CCM's control are such that CCM assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of the CCM product(s) must test the product(s) for suitability for the intended application and purpose before proceeding the full application of the product(s). CCM reserves the right to change the properties of its products without notice. All sales of CCM product(s) are subject to its current terms and conditions of sale.

Prior to each use of any CCM product, the user must always read and follow the warnings and instructions on the product's most current Technical Data Sheet, product label and Safety Data Sheet which are available at www.ccmaterial.com. Nothing contained in any CCM materials relieves the user of the obligation to read and follow the warnings and instruction for each CCM product as set forth in the current Technical Data Sheet, product label and Safety Data Sheet prior to product use.

CCM warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Technical Data Sheet when used in accordance with the written instructions. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor.

NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. CCM SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. CCM SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.