

FasTrac CE450 Novolac Coating

HIGH CHEMICAL RESISTANCE NOVOLAC COATING



Technical Data Sheet

PRODUCT DESCRIPTION

FasTrac CE450 Novolac Grout is a 100% solids, novolac epoxy coating for aggressive chemical exposure environments. FasTrac CE450 Novolac Coating may be used in both horizontal and vertical applications on both steel and concrete substrates and can be used as non-skid coating with the use of a dried broadcast sand.

APPLICATIONS

- **Concrete And Steel Surfaces**
- **Secondary Containment**
- **Chemical Pump and Equipment Foundations**

Substrates must be thoroughly dry before use.

Sumps, Pits and Holding Ponds

FEATURES

- **Highly Chemical Resistant**
- Roller, Brush, or Squeegee Application
- Vertical and Horizontal Use
- 100% Solids

SURFACE PREPARATION

Substrate shall be a minimum 40°F (4.4°C) at time of application. Concrete surfaces shall be prepared to a Concrete Surface Profile (CSP) of 3 or greater in accordance with ICRI Standard 310.2R. Remove all dust, debris, grease and bond-inhibiting compounds from concrete and steel surfaces. Steel surfaces shall be blasted to an SSPC-SP6 commercial finish.

MIXING

Pre-mix Components A and B for 30 seconds. Combine Components A and B at a 2: 1 ratio (by volume) in a suitable size mixing container. Use marked measuring containers to ensure proper ratios. Mix for 3 minutes using drill and jiffy / paint paddle attachment. Do not whip air into coating during mixing. Use coating immediately after mixing. Do not thin coating with solvents.

APPLICATION

Apply coating evenly and uniformly using a squeegee, brush, or roller, starting in one area and working outward. For single coat applications, apply at 20 mil thickness or as specified. Ensure coating is applied within working time of material (approximately 35 minutes at 75°F). For multiple layer applications, apply a second coating within the appropriate recoat time.

CURING

Coating is self-curing. In service operation may begin within 24 to 72 hours, depending upon cure and substrate temperatures and exposure conditions.

CLEAN UP

All surfaces, tools and equipment may be cleaned with MEK, acetone or similar solvent prior to coating hardening.





www.fastracproducts.com



816-380-4747



sales@fastracproducts.com



👤 Lee's Summit, MO 64081



FasTrac CE450 Novolac Coating

HIGH CHEMICAL RESISTANCE NOVOLAC COATING

PACKAGING AND COVERAGE

3 Gallon Unit covers approximately 240 square feet at 20 mil thickness. Coverage will vary depending upon substrate profile and porosity. Storage temperatures - 50°F to 90°F (10°C to 32°C).

SHELF LIFE

2 years in original unopened containers when stored in dry, weatherproof conditions.

	_	TVDICAL DD	OPERTIES at 75°	P F (23 8° C)		
TEST METHO	DD	TIFICAL FRO	JERTILS at 75	1 (23.0 0)	RESULTS	
ASTM D2240 Ha	80-90					
ASTM D638 Ter	5,600 psi (38.6 MPa)					
ASTM D695 Cor	10,000 psi (68.9 MPa)					
Applied Thickne	20 mil +/- 5mil					
Pot Life	30-40 minutes					
Color	Light Gray					
Recoat Times						
				50°F(10°C)	8 Hours Min 2 Days Max	
				70°F (21°C)	3 Hours Min 2 Days Max	
				90°F (32°C)	30 Minutes Min 24 Hours Max	
		CHEMICA	AL RESISTANCE	CHART		
SOLVENTS		ORGANICS ACIDS (CONC.)		BASES	BASES / ALKALINES (CONC.)	
Acetaldehyde	Isopropyl Alcohol	Acetic (1-50%)	Engravers (1-50%	Ammonia (1-25%)	Dimethyl Aniline	
Asstans	let Firel	Acid plating solutions	Hydrochloric (1-37%)	Ammonium Hydroxide (1-	Hydrogen Peroxide (1-	

CHEMICAL RESISTANCE CHART								
SOLVENTS		ORGANICS ACIDS (CONC.)		BASES / ALKALINES (CONC.)				
Acetaldehyde	Isopropyl Alcohol	Acetic (1-50%)	Engravers (1-50%	Ammonia (1-25%)	Dimethyl Aniline			
Acetone	Jet Fuel	Acid plating solutions	Hydrochloric (1-37%)	Ammonium Hydroxide (1- 25%	Hydrogen Peroxide (1- 30%)			
Acetonitrile	Kerosene	Adipic (1-25%)	Hydrofluoric (1-40%)	Aniline	Green Pulp Liquor			
Acrylonitrile	Methyl Ethyl Ketone	Azotic (1-50%)	Mattling (1-98%)	Barium Hydroxide (1-sat.)	Soap solutions			
Butyl acetate	Methanol	Battery (1-98%)	Nitric (1-50%)	Black Pulp Liquor	Sodium Cyanide (1-15%)			
Cyclohexane	Methyl Alcohol	Chromic (1-30%)	Oil of vitriol (1-98%)	Butyl Amine	Sodium Hypochlorite (1- 9%)			
Ethanol	Rubbing Alcohol	Chlorohydric (1-37%)	Oleic	Cadmiun Cyanide Plating	Sodium Hydroxide (1-50%)			
Ethyl acetate	Wood Alcohol	Dibasic (1-sat.)	Phosphoric (1-85%)	Calcium Hydroxide (1-25%)	Triethanolamine			
Ethyl alcohol	1,1,1 Trichloroethane	Ethanoic (1-50%)	Sulfuric (1-98%)	Chromium Trioxide (1-25%	Triethylamine			
Formaldehyde	Phenol	Ethylic (1-50%)	Vitriol (1-98%)	Copper Cyanide Plating	Potassium Hydroxide (1- sat)			

HEALTH AND SAFETY INFORMATION

Product contains epoxy resin and amines. Wear proper PPE when using this product, including eye protection, gloves, skin protection and NIOSH / MHSA approved respirator. Read SDS thoroughly before use. Prop 65: This product contains chemicals known to the state of California to cause cancer

LIMITED WARRANTY

LIMITED WARRANTY All information provided by Cornerstone Construction Material LLC (CCM) concerning CCM products, including but not limited to, any recommendations and advice relating to the application and use of CCM products, is given in good faith based on CCM's current experience and knowledge of its products when properly stored, handled, and applied under normal conditions in accordance with CCM's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of CCM's control are such that CCM assumes no liability for the provision of such information, advice, recommendations, or instructions related to its products, no shall any legal relationship be recreated by or arise from the provision of such information, advice, recommendations, or instructions related to its products. The user of the CCM product[s) is unstable that the product of the product of the product is considered by a product of the product of the product is considered by a product of the product of the product is considered by a product of the product of the product is considered by a product of the product is a product of the current Technical Data Sheet, product Label and Safety Data Sheet when used in accordance with the urrent Technical Data Sheet when used in accordance with the written instructions. User determines suitability of product for intended use and assumes all rivisions. The business of the product of the product Data Sheet when used in accordance with the written

Every reasonable effort is made to apply exacting standards both in the manufacture of "FasTrac CE450 Novolac Coating" product and in the information which we issue concerning these products and their use. We warrant our products to be good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only on quality products, but also upon many factors beyond our control. Therefore, expect for such pelacement or refund, Connerstone Construction Material LLC (CCM) makes no warranty or guarantee, express or implied, including warranties of filters for a particular purpose or merchantability, respecting to some construction that refund the products, and Connerstone Construction Material LLC (CM) that is a construction of the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the Cornerstone Construction Material LLC (CCM) technical manager.

Revised: 1-15-2024 SR



