

FasTrac CE550 SBA

SEGMENTAL BRIDGE ADHESIVE



Technical Data Sheet

PRODUCT DESCRIPTION

FasTrac Ce550 SBA is a two component, high modulus, moisture insensitive epoxy designed to bond and seal precast bridge segments. CE550 is available in three versions, including a low temperature, normal and high temperature formula. CE550 meets the requirements of ASM C 881 Types VI and VII.

APPLICATIONS

- Bonding Bridge Segments
- Sealing Bridge Segments
- Cold and Hot Weather Bonding

SURFACE PREPARATION

FEATURES

- Non-Sag
- High Modulus
- Moisture Insensitive

Concrete surfaces must be clean, sound, and free of all bond inhibiting contaminants. Dust, laitance, grease, curing compounds and coatings must be removed prior to application. Surfaces may be damp but the best performance is achieved when dry.

MIXING

Pre-condition Components A and B to between 65°F and 75°F (18.3°C and 23.8°C). Pre-mix Components A and B using drill and paddle. Pour all of Component B into pail containing Component A and mix for 3 minutes until a uniform gray color with no streaks is achieved. Do not whip air into components during mixing. Use immediately after mixing.

INSTALLATION

Apply to specified thickness using gloved hand, trowel, or similar tool. Typical thickness ranges from 1/8 inch to 1/16 inch. Work product into substrate to ensure full contact and wetting of surfaces. Bonding should be accomplished via application in both segments unless otherwise specified. Ensure joining and bonding occurs within the pot life of the epoxy.

CURING

Product is self-curing. Do not add solvents. Protect from freezing temperatures, rain and traffic until minimum strength requirements are achieved.

CLEAN UP

All surfaces, tools and equipment may be cleaned with FasTrac Finishing Aid or a solvent based cleaner prior to material setting.



www.fastracproducts.com

- 🔇 816-380-4747
- 🔀 sales@fastracproducts.com
- Lee's Summit, MO 64081



PACKAGING AND YIELD

3 gallon (11.34 liters) units. Coverage at an application thickness of 1/16 inch is approximately 26 square feet (2.4 square meters).

SHELF LIFE AND STORAGE

2 year shelf life when stored in dry, weatherproof conditions. Storage temperatures 40°F to 95°F (4.4°C to 35°C).

TYPICAL	. PROPERTIES at 75	° F	(23.8°	C)	
---------	--------------------	-----	--------	------------	--

TEST METHOD	RESULTS	
ASTM C881 Consistency	¼ inch (6.0 mm) no sag	
ASTM C881 Gel Time	45 minutes	
Open Time (65°F, 85°F, 115°F LT, NT, HT formulas)	60 minutes	
ASTM C882 Contact Strength		
	1 Day	1,400 psi (9.7 MPa)
ASTM D695 Compressive Strength		
	1 Day	3,000 psi (20.7 MPa)
	2 Day	7,000 psi (48.3 MPa)
ASTM C882 Bond Strength		
	2 Day Moist	1,400 psi (9.7 MPa)
ASTM D648 Heat Deflection Temperature	140 °F (60 °C)	

HEALTH AND SAFETY INFORMATION

Product contains epoxy resin and amines. Wear proper PPE when using this product, including gloves, eye and skin protection and NIOSH / MSHA approved respirator or dust mask. Read SDS thoroughly before use. Prop 65: This product contains chemicals known by the state of California to cause cancer.

LIMITED WARRANTY

LIMITED WARRANTY All information provided by Cornerstone Construction Material LLC (CCM) concerning CCM products, including but not limited to, any recommendations and advice relating to the application and use of CCM products, is given in good faith based on CCM's current experience and knowledge of its products when properly stored, handledg, and applied under normal conditions in accordance with CCM's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of CCM's control are such that CCM assumes no liability for the provision of such information, advice, recommendations, or instructions related to its products), must test term and conditions of all conditions related to its products. The bit is products for the intended application and purpose before proceeding the full application of the product(s). (CM reserves the right to change the properties of its products whom notice. All sales of CCM product(s) are subject to its current terms and conditions of sale. Prior to each use of any CCM product, the are valible at and follow the warming and instructions for each CCM application for a such contrastication. Notification and source and follow the variant and follow the warming and instructions for each CCM product taked and Select to a such contrastication. Notification and applied to be face from manufacturing defects and to low the warming and instructions for each CCM product taked and Select to be face form manufacturing defects and to meet the technical properties on the current Technical Data Sheet, product taked and Select to reverse the right to change the proposed of the face of the instructions. User determines subtability of product for installations to be fee form manufacturing defects and to meet the technical properties on the current Technical Data Sheet, the written instructions. User determines subtability of product set in instructions. The written instructions for each CMAN WARRANTY ANY WARRANTT

Every reasonable effort is made to apply exacting standards both in the manufacture of "FasTrac CE550" product and in the information which we issue concerning these products and their use. We warrant our products to be good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only on quality products, but also upon many factors beyond our control. Therefore, except for synuth replacement or refund, Conrestone Construction Material LLC (CM) makes no warranty or guarantee, express or implied, including warrantes of fitness or a particular purpose or merchantability, respecting its products, and Cornerstone Construction Material LLC (CM) makes no warranty or guarantee, express or implied, including warrantes of fitness and the set of a particular purpose or merchantability, respecting its products, and Cornerstone Construction Material LLC (CM) makes no warranty or guarantee, express or implied, including warrantes of fitness. A construction Material LLC (CM) makes no warranty or guarantee is the set of the state and the state and the set of the state and the state and the set of the state and the state and the set of the state and the set of

Revised: 2-28-2024_SR

CEMENTS | CONCRETES | EPOXIES | GROUTS | MORTARS | MIXING SYSTEMS | HFST

816-380-4747

📈 sales@fastracproducts.com

