



# FasTrac CE308 Epoxy Anchor Gel

HIGH-STRENGTH EPOXY ANCHORING ADHESIVE



## Technical Data Sheet

### PRODUCT DESCRIPTION

FasTrac CE308 Epoxy Anchor Gel is a non-sag, 100% solids, two component anchoring adhesive that meets the requirements of ASTM C 881 and AASHTO M 235 Types I, II, IV and V, Grade 3, Classes B and C. FasTrac CE 308 Epoxy Anchor Gel provides high strengths and excellent bond development for tensile load applications.

### APPLICATIONS

- Anchors and Dowels
- Setting Injection Ports
- Crack Sealing
- Structural Bonding
- Dry or Damp Applications

### FEATURES

- High Modulus
- Non-Sag Gel
- 1:1 Cartridge / Mix Ratio
- High Bond Strengths
- Moisture Tolerant

### PREPARATION

Drill specified sized hole based upon design depth and diameter. Blow out hole with oil-free compressed air. Insert wire brush into hole and scour all sides and bottom of drilled hole to loosen all drilling dust and debris. Blow out hole a second time with oil free compressed air until no dust or debris is observed exiting hole. Holes should be free of standing water and completely dry. Holes may be slightly damp but that may affect overall property development. Anchors, bolts, and dowels should be free of oils, grease and oxidation. Remove all substances that can inhibit the bond of epoxy to anchor.

### MIXING & INSTALLATION

Best mixing and use are achieved when adhesive is between 65°F and 85°F (18.3°C and 29.4°C). For cartridges, install static mixer on cartridge ensuring positive seal. Cut tip as necessary. Begin dispensing using a 1:1 ratio manual or automated gun until a uniform color exits static mixer. Discard any material that is not of a uniform color. Starting at bottom of hole, dispense adhesive and slowly move upward through hole. Do not begin dispensing adhesive from top of hole. Fill hole uniformly to approximately 2/3 full and insert anchor immediately. Anchors should be slowly rotated during insertion to promote wetting of anchor surfaces and minimize air entrapment. For larger packaged units, mix material at a 1:1 ratio in a clean, suitable sized container using slow speed drill and paddle until a uniform color is achieved. Do not whip air into adhesive during mixing. Use material immediately after mixing.

### CURING

FasTrac CE308 Epoxy Anchor Gel is self-curing. Do not add solvents during cure. Protect from rain and freezing temperatures until design strengths are achieved. Best property development occurs when temperatures are between 70°F and 90°F (21°C and 32°C).

### CLEAN UP

All surfaces, tools and equipment may be cleaned with water and detergent prior to adhesive setting.

### PACKAGING, STORAGE AND SHELF LIFE

8.4 ounce (248 ml), 20.3 ounce (600 ml) and 50.7 ounce (1500 ml) cartridges, 1 Gallon (3.78 liter), 2 Gallon (7.57 liter) and 10 Gallon (37.85 liter) units. 2 years when stored under weatherproof conditions. Storage temperatures - 50°F to 90°F (10°C to 32°C).



 [www.fastracproducts.com](http://www.fastracproducts.com)

 816-380-4747

 [sales@fastracproducts.com](mailto:sales@fastracproducts.com)

 Lee's Summit, MO 64081



# FasTrac CE308 Epoxy Anchor Gel

HIGH-STRENGTH EPOXY ANCHORING ADHESIVE

TYPICAL PROPERTIES at 75° F (23.8° C)	
TEST METHOD	RESULTS
Viscosity	¼ inch non - sag gel
ASTM D695 Compressive Strength (7 Days)	12,500 psi (86.2 MPa)
ASTM D695 Compressive Modulus (7 Days)	300,000 psi (2069 MPa)
ASTM C882 Slant Shear Bond (1 Day)	2,000 psi (13.8 MPa)
ASTM C882 Slant Shear Bond (7 Days)	2,500 psi (17.2 MPa)
ASTM D638 Tensile Strength	7,500 psi (51.7 MPa)
ASTM D638 Tensile Elongation	1.2%
ASTM D732 Shear Strength	2,800 psi (19.3 MPa)
ASTM C884 Thermal Compatibility	PASS
ASTM D648 Heat Deflection Temperature	140°F (60°C)

ESIMATING GUIDE & TENSION LOADS								
ROD DIA. IN.(MM)	DRILL BIT DIA. IN.(MM)	EMBED. DEPTH IN.(MM)	HOLES PER 600ML (250ML) CART.	TENSION LOAD BASED ON BOND STRENGTH		ALLOWABLE TENSION LOAD LBS.(KN) BASED ON STEEL STRENGTH		
				ULTIMATE LBS.(KN)	ALLOWABLE LBS.(KN)	F1554 GRADE 36	A193 GRADE B7	F593 304SS
3/8 (9.5)	1/2 (12.7)	3 3/8 (8.6)	115 (50)	9,800 (43.6)	2,450 (10.9)	2,105 (9.4)	4,535 (20.2)	3,630 (16.1)
1/2 (12.7)	5/8 (15.9)	4 1/2 (11.4)	65 (25)	16,400 (73.0)	4,100 (18.2)	3,750 (16.7)	8,080 (35.9)	6,470 (28.8)
5/8 (15.9)	3/4 (19.1)	5 5/8 (14.3)	30 (15)	25,200 (112.1)	6,300 (28.0)	5,875 (26.1)	12,660 (56.3)	10,120 (45.0)
3/4 (19.1)	7/8 (22.2)	6 3/4 (17.1)	18 (7)	36,000 (160.1)	9,000 (40.0)	8,460 (37.6)	18,230 (81.1)	12,400 (55.2)
7/8 (22.2)	1 (25.4)	7 7/8 (20.0)	15 (6)	48,000 (213.5)	12,000 (53.4)	11,500 (51.2)	24,785 (110.2)	16,860 (75.0)
1 (25.4)	1 1/8 (28.6)	9 (22.9)	10 (4)	62,000 (275.8)	15,500 (69.0)	15,025 (66.8)	32,380 (144.0)	22,020 (97.9)
1 1/4 (31.8)	1 3/8 (34.9)	11 1/4 (286)	6 (3)	96,000 (427.0)	24,000 (106.8)	23,490 (104.5)	50,620 (225.2)	34,420 (153.1)

## HEALTH AND SAFETY INFORMATION

This product contains Portland cement, silica sand and respirable silica. Respirable silica is a suspected human carcinogen by NTP and IARC. Use proper PPE when working with this material, including eye protection, gloves and NIOSH / MSHA approved dust masks or respiratory protection as required to prevent inhalation and accidental ingestion. Read SDS thoroughly before use.

## LIMITED WARRANTY

LIMITED WARRANTY All information provided by Cornerstone Construction Material LLC (CCM) concerning CCM products, including but not limited to, any recommendations and advice relating to the application and use of CCM products, is given in good faith based on CCM's current experience and knowledge of its products when properly stored, handled, and applied under normal conditions in accordance with CCM's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of CCM's control are such that CCM assumes no liability for the provision of such information, advice, recommendations, or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations, or instructions related to its products. The user of the CCM product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s). CCM reserves the right to change the properties of its products without notice. All sales of CCM product(s) are subject to its current terms and conditions of sale. Prior to each use of any CCM product, the user must always read and follow the warnings and instructions on the product's most current Technical Data Sheet, product label and Safety Data Sheet which are available at [www.ccmaterial.com](http://www.ccmaterial.com). Nothing contained in any CCM materials relieves the user of the obligation to read and follow the warnings and instructions for each CCM product as set forth in the current Technical Data Sheet, product label and Safety Data Sheet prior to product use. CCM warrants this product for one year from the date of installation to be free from manufacturing defects and to meet the technical properties on the current Technical Data Sheet when used in accordance with the written instructions. User determines suitability of product for intended use and assumes all risks. The buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. CCM SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. CCM SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Every reasonable effort is made to apply exacting standards both in the manufacture of "FasTrac CE308 Epoxy Anchor Gel" product and in the information which we issue concerning these products and their use. We warrant our products to be good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only on quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, Cornerstone Construction Material LLC (CCM) makes no warranty or guarantee, express or implied, including warranties of fitness for a particular purpose or merchantability, respecting its products, and Cornerstone Construction Material LLC (CCM) shall have no other liability with respect thereto. Any claim regarding a product defect must be received in writing within one year of the date of shipment. No claim will be considered without such written notice or after the specified time interval. The User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the Cornerstone Construction Material LLC (CCM) technical manager.

Revised: 4-8-2024\_SR

CEMENTS | CONCRETES | EPOXIES | GROUTS | MORTARS | MIXING SYSTEMS | HFST



[www.fastracproducts.com](http://www.fastracproducts.com)



816-380-4747



[sales@fastracproducts.com](mailto:sales@fastracproducts.com)



Lee's Summit, MO 64081