



FasTrac AquaGrout

UNDERWATER CEMENTITIOUS GROUT



Technical Data Sheet

PRODUCT DESCRIPTION

FasTrac AquaGrout is a high strength, cementitious grout for underwater and tidal zone use. A highly pumpable and versatile material, FasTrac AquaGrout may be placed from plastic to fluid consistencies for pile encapsulation, underwater grouting, and tidal zone re-pointing applications.

APPLICATIONS

- Pile Encapsulation
- Underwater Grouting
- Tidal Zone Re-Pointing
- Underwater Repairs and Void Filling

FEATURES

- Placement Versatility
- Excellent Underwater Bond Development
- Highly Pumpable
- High Strength

SURFACE PREPARATION

All concrete surfaces shall be free of marine growth, coatings and any substances that will prevent bonding. Underwater tools may be required to achieve a satisfactory clean condition. Maximum bond development is achieved when a clean and roughened substrate surface is attained following ICRI Standard 310.2R Selecting and Specifying Concrete Surface Preparation for Sealers, Coatings, Polymer Concretes and Concrete Repair using a Concrete Surface Profile (CSP) of 6 to 10. For tidal zone applications, presoak concrete surfaces for 4 – 8 hours prior to material installation.

FORMWORK

All formwork must be rigidly secured and watertight. Seal all internal formwork joints. For pile encapsulation, ensure pile jackets have appropriately sized spacers and bottom seal is strong enough and properly sealed to hold weight of grout. Ports should be spaced every 2 to 3 feet (0.61 to 0.91 meters) or as specified on drawings.

MIXING

For multiple bag mixes, a mortar mixer is required (not cement mixer). Start by adding approximately 3 quarts (2.8 liters) per 50 lb.(22.7 kg.) and add additional water to bring the consistency to a fluid, yet cohesive mix. Do not exceed 4.1 quarts (3.88 liters) of water.

INSTALLATION

Pump grout into formwork through ports or tremie pour into formed area or jacket. Do not allow the grout to freefall more than 5 feet through water.

CURING

No curing is required for underwater placements. For tidal zone applications, wet cure for 24 to 48 hours or use an approved curing compound meeting the requirements of ASTM C 309.



 www.fastracproducts.com

 816-380-4747

 sales@fastracproducts.com

 Lee's Summit, MO 64081



FasTrac AquaGrout

UNDERWATER CEMENTITIOUS GROUT

CLEAN UP

All surfaces, tools and equipment may be cleaned with water prior to material setting.

COVERAGE AND YIELD

50 lb. (22.7 kg) bag yields 0.43 cubic feet (0.012 cubic meters) at a near fluid consistency.

Also available in 2000 lb. (909 kg) bulk bags.

SHELF LIFE AND STORAGE

Shelf life: 1 year from date of manufacture when stored in dry weatherproof conditions.

Storage Temperatures: 40° F (4°C) to 90° F (32° C).

Best results obtained when material is pre-conditioned to between 55° F and 80° F (12.7°C and 26.7°C).

TYPICAL PROPERTIES at 75° F (23.8° C)

TEST METHOD		RESULTS		
		DRYPACK	FLOWABLE	NEAR FLUID
ASTM C109 Compressive Strength				
	1 Day	7,000 psi (48.2 MPa)	3,000 psi (20.7 MPa)	2,500 psi (17.2 MPa)
	7 Days	9,500 psi (65.5 MPa)	5,500 psi (37.9 MPa)	5,000 psi (34.5 MPa)
	28 Days	10,000 psi (68.9 MPa)	7,500 psi (51.7 MPa)	7,000 psi (48.2 MPa)
ASTM C882 Slant Shear Bond				
	1 Day	2,000 psi (13.8 MPa)		
	7 Days	2,500 psi (17.2 MPa)		
ASTM C266 Set Time				
		4 to 6 hours	5 to 7 hours	6 to 8 hours

HEALTH AND SAFETY INFORMATION

This product contains Portland cement, silica sand and respirable silica. Respirable silica is a suspected human carcinogen by NTP and IARC. Use proper PPE when working with this material, including eye protection, gloves and NIOSH / MSHA approved dust masks or respiratory protection as required to prevent inhalation and accidental ingestion. Read SDS thoroughly before use.

LIMITED WARRANTY

LIMITED WARRANTY All information provided by Cornerstone Construction Material LLC (CCM) concerning CCM products, including but not limited to, any recommendations and advice relating to the application and use of CCM products, is given in good faith based on CCM's current experience and knowledge of its products when properly stored, handled, and applied under normal conditions in accordance with CCM's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of CCM's control are such that CCM assumes no liability for the provision of such information, advice, recommendations, or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations, or instructions related to its products. The user of the CCM product(s) must test the product(s) for suitability for the intended application and purpose before proceeding the full application of the product(s). CCM reserves the right to change the properties of its products without notice. All sales of CCM product(s) are subject to its current terms and conditions of sale. Prior to each use of any CCM product, the user must always read and follow the warnings and instructions on the product's most current Technical Data Sheet, product label and Safety Data Sheet which are available at www.ccmaterial.com. Nothing contained in any CCM materials relieves the user of the obligation to read and follow the warnings and instructions for each CCM product as set forth in the current Technical Data Sheet, product label and Safety Data Sheet prior to product use. CCM warrants this product for one year from the date of installation to be free from manufacturing defects and to meet the technical properties on the current Technical Data Sheet when used in accordance with the written instructions. User determines suitability of product for intended use and assumes all risks. The buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. CCM SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. CCM SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Every reasonable effort is made to apply exacting standards both in the manufacture of "FasTrac AquaGrout" product and in the information which we issue concerning these products and their use. We warrant our products to be good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only on quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, Cornerstone Construction Material LLC (CCM) makes no warranty or guarantee, express or implied, including warranties of fitness for a particular purpose or merchantability, respecting its products, and Cornerstone Construction Material LLC (CCM) shall have no other liability with respect thereto. Any claim regarding a product defect must be received in writing within one year of the date of shipment. No claim will be considered without such written notice or after the specified time interval. The User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the Cornerstone Construction Material LLC (CCM) technical manager.

10-27-2025_SR

CEMENTS | CONCRETES | EPOXIES | GROUTS | MORTARS | MIXING SYSTEMS | OVERLAYS

Western Material Design · 1150 SE Hamblen Road, Lee's Summit, MO 64081