

Chemical Resistance Chart

Key: A Splash & Spill or Immersion Service
 B Splash & Spill Service
 F Not Recommended
 Contact FasTrac Construction Products for all elevated temperature service conditions

Chemical Name	Resistance
Acetic Acid 0% - 20%	B
Acetic Acid +25%	F
Acetone	F
Acrylic Acid	F
Aluminum Sulfate	A
Ammonium Chloride	A
Ammonium Hydroxide 25%	A
Ammonium Nitrate	A
Benzene	F
Black Liquor	B
Boric Acid	A
Calcium Chloride	A
Calcium Hydroxide	A
Chlorine	F
Chromic Acid 0% - 20%	B
Citric Acid 0% - 50%	A
Cyclohexane	A
Ethyl Alcohol	A
Ethylene Dichloride	F
Ethylene Glycol	A

Chemical Name	Resistance
Ferric Sulfate	A
Formaldehyde	A
Gasoline	A
Hexane	A
Hydrobromic Acid 0% - 25%	B
Hydrochloric Acid 37%	A
Hydrochloric Acid	B
Hydrofluoric Acid	F
Hydrogen Sulfide	F
Isopropyl Alcohol	A
Kerosene	A
Maleic Acid	F
Methyl Alcohol	A
Methylene Chloride	F
MEK	F
Naptha	A
Nitric Acid 0% - 8%	B
Nitric Acid + 8%	F
Perchlorethylene	A
Phenol	F

Chemical Resistance Chart

Key: A Splash & Spill or Immersion Service
 B Splash & Spill Service
 F Not Recommended
 Contact FasTrac Construction Products for all elevated temperature service conditions

Chemical Name	Resistance
Phosphoric Acid 0% - 25%	B
Phosphoric Acid +25%	F
Potassium Carbonate	A
Potassium Fluoride	B
Potassium Hydroxide	A
Potassium Permanganate	A
Potassium Sulfate	A
Potassium Glycol	A
Salt Water	A
Sodium Bicarbonate	A
Sodium Bisulfate	A
Sodium Bisulfite	A
Sodium Chloride	B
Sodium Fluoride	B
Sodium Hydroxide 0% - 50%	B
Sodium Hypochlorite	F
Sodium Sulfate	A
Sodium Sulfite	A
Stearic Acid	A
Sulfuric Acid 0% - 50%	B

Chemical Name	Resistance
Sulfuric Acid >50%	F
Tetrahydrofuran	F
Toluene	F
Trichloroethylene	F
Turpentine	F
Xylene	F

