



FasTrac CE700 HPC Patching

HYBRID POLYMER CONCRETE PATCHING KIT



Technical Data Sheet

PRODUCT DESCRIPTION

FasTrac CE700 HPC Patching is a three component, high performance, hybrid polymer patching system for concrete pavements, bridge decks and similar repairs. FasTrac CE700 HPC Patching is a highly durable, impermeable repair that allows return to traffic in 2 to 3 hours. FasTrac CE700 HPC Patching provides excellent abrasion resistance, high tensile strengths, requires no primer and contains no VOC's. Ranked #1 in a recent National Road Research Alliance (NRRRA) study of patching materials, FasTrac CE700 HPC Patching is the ideal long-term solution for road and bridge deck patching.

APPLICATIONS

- Parking Deck Repairs
- Grade Corrections
- Pavement Spall Repair
- Bridge Deck Patching

FEATURES

- Return to Traffic in 2 to 3 Hours
- Strong Like Concrete, Flexible Like Asphalt
- No VOCs
- No Primer Required

SURFACE PREPARATION

Condition surfaces to a minimum 50°F (10°C) and above for best results. Minimum substrate temperature is 40°F (4.4°C). Concrete surfaces should be structurally sound and mechanically profiled to a Concrete Surface Profile (CSP) of 6 or greater in accordance with ICRI Standard 310.2R Selecting and Specifying Concrete Surface Preparation for Coatings, Sealers and Polymer Overlays. Shotblasting or similar means is recommended. All loose, broken, or unsound concrete must be removed. Blow out concrete surfaces of all dust, debris, and bond inhibiting contaminants. Concrete surfaces should be thoroughly dry and free of all standing water prior to product installation. Exposed rebar should be blasted clean to remove all rust, scale and oxidation.

MIXING

Mix only an amount of material that can be used within its pot life. Proportion each liquid component (Components A and B) at a 1 : 1 ratio into a suitable size mixing container. Mix liquids thoroughly for 3 minutes with a Jiffy mixer on low speed (400-600rpm). Do not whip air into liquids. Scrape the sides and bottom of the container. Slowly add Component C (aggregate) while mixing to achieve desired consistency. Mix until all aggregate is wetted out and no dry pockets remain. Use immediately after mixing.

INSTALLATION

Place patch full depth from one side of repair and fill along patch geometry. Level and screed as necessary with steel trowel. FasTrac Epoxy Cleaner / Finishing Aid sprayed on tools will aid in reducing tool drag during leveling and finishing. When used as an overlay, place FASTRAC CE700 HPC Patching with a vibratory strike off screed or slipform paver as appropriate for the application. When using optional friction aggregate, broadcast aggregate and lightly float or roll it into freshly placed FASTRAC CE700 HPC Patching.

CURING

FasTrac CE700 HPC Patching is a self-curing material. Do not wet cure. Protect from rain and freezing temperatures until minimum strengths are developed.

CLEAN UP

Clean tools and equipment immediately after final use with FasTrac Epoxy Cleaner / Finishing Aid or FasTrac Natural Clean.



 www.fastracproducts.com

 816-380-4747

 sales@fastracproducts.com

 Lee's Summit, MO 64081



FasTrac CE700 HPC Patching

HYBRID POLYMER CONCRETE PATCHING KIT

PACKAGING AND YIELD

- **0.5 cu. ft.:** 0.5-gallon Part A – liquid / 0.5-gallon Part B-liquid / 50 lb. Part C – Aggregate
- **1.0 cu. ft.:** 1.0-gallon Part A - liquid / 1.0-gallon Part B - liquid / 2 - 50 lb. bags Part C - Aggregate
- **5.0 cu. ft.:** 5.0-gallon Part A - liquid (pail) / 5.0-gallon Part B - liquid (pail) / 10 - 50 lb. bags Part C – Aggregate
- **CE700 HPC Patching / Overlay Volumetric Mixing (per ~1.0 cu. yd.):**
 - 50 gallons liquid (25 gallons Part A, 25 gallons Part B) 3000 lb. Part C-aggregate

SHELF LIFE AND STORAGE

Shelf life: 2 years from date of manufacture when stored in dry weatherproof conditions.

Storage Temperatures: 40° F (4.4°C) to 95° F (35° C).

TYPICAL PROPERTIES at 75° F (23.8° C)

TEST METHOD	RESULTS
ASTM C1583 / ACI 503R Bond Strength	>250 psi (1.7 MPa) (Substrate Failure)
ASTM C579 Compressive Strength	>5,000 psi (34.5 MPa)
ASTM D638 Tensile Elongation	>50%
ASTM D638 Tensile Strength	2,500 psi (17.2 MPa)
ASTM C884 Thermal Compatibility	Pass
ASTM C531 Shrinkage	0.01%
AASHTO T277 Chloride Ion Permeability	0.0 coulombs
ASTM D 570 Absorption	0.2% (polymer only)
ASTM C579 Compressive Modulus	< 500,00 psi (3447 MPa)
ASTM D695 Compressive Modulus	< 90,000 psi (620 MPa)

CURE TIME

TEMPERATURE

	60°F (15.5°C)	65°F (18.3°C)	70°F (23.8°C)	75°F (23.8°C)	80°F (26.6°C)	85°F (29.4°C)	90°F (32°C)	95° (35°C)
Cure Time (Standard)	5 Hours	4 Hours	3.5 Hours	3 Hours	2 Hours	1.5 Hours	1 Hours	0.5 Hours
Cure Time (Accelerated)	4 Hours	3 Hours	2.5 Hours	2 Hours	1.5 Hours	1 Hours	.5 Hours	0.25 Hours

HEALTH AND SAFETY INFORMATION

This product contains silica sand and respirable silica. Respirable silica is a suspected human carcinogen by NTP and IARC. Use proper PPE when working with this material, including eye protection, gloves and NIOSH / MSHA approved dust masks or respiratory protection as required to prevent inhalation and accidental ingestion. Read SDS thoroughly before use. Proposition 65 - This product contains material listed by the state of California as known to cause birth defects or other reproductive harm.

LIMITED WARRANTY

LIMITED WARRANTY All information provided by Cornerstone Construction Material LLC (CCM) concerning CCM products, including but not limited to, any recommendations and advice relating to the application and use of CCM products, is given in good faith based on CCM's current experience and knowledge of its products when properly stored, handled, and applied under normal conditions in accordance with CCM's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of CCM's control are such that CCM assumes no liability for the provision of such information, advice, recommendations, or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations, or instructions related to its products. The user of the CCM product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s). CCM reserves the right to change the properties of its products without notice. All sales of CCM product(s) are subject to its current terms and conditions of sale. Prior to each use of any CCM product, the user must always read and follow the warnings and instructions on the product's most current Technical Data Sheet, product label and Safety Data Sheet which are available at www.ccmaterial.com. Nothing contained in any CCM materials relieves the user of the obligation to read and follow the warnings and instructions for each CCM product as set forth in the current Technical Data Sheet, product label and Safety Data Sheet prior to product use. CCM warrants this product for one year from the date of installation to be free from manufacturing defects and to meet the technical properties on the current Technical Data Sheet when used in accordance with the written instructions. User determines suitability of product for intended use and assumes all risks. The buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. CCM SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. CCM SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Every reasonable effort is made to apply exacting standards both in the manufacture of "FasTrac CE700 HPC Patching Kit" product and in the information which we issue concerning these products and their use. We warrant our products to be good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only on quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, Cornerstone Construction Material LLC (CCM) makes no warranty or guarantee, express or implied, including warranties of fitness for a particular purpose or merchantability, respecting its products, and Cornerstone Construction Material LLC (CCM) shall have no other liability with respect thereto. Any claim regarding a product defect must be received in writing within one year of the date of shipment. No claim will be considered without such written notice or after the specified time interval. The User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the Cornerstone Construction Material LLC (CCM) technical manager.

4-24-2026_SR

CEMENTS | CONCRETES | EPOXIES | GROUTS | MORTARS | MIXING SYSTEMS | HFST

Cornerstone Construction Materials · 1150 SE Hamblen Road, Lee's Summit, MO 64081